

# VIVE EMULSION

## Emulsion Paint for Interior Use



### DESCRIPTION

**VIVE EMULSION** is an emulsion paint for interior use, suitable for surfaces such as walls, ceilings, stairs, warehouses. It represents the economic and reliable solution for areas where frequent painting and freshening up is needed such as hotels, schools, hospitals, big public works, by offering a guaranteed result at an exceptional price. It is quick drying and is recoated rapidly. It exhibits good stain resistance, good washability and maintains its properties even at low temperatures. It combines great whiteness and coverage with ease of application and very good levelling properties.

**Great Whiteness & Coverage**

**Ideal for Frequent Painting**

### PRODUCT INFORMATION

**Type:** Emulsion paint.

**Specific gravity:** 1,57 ± 0,02 gr/cm<sup>3</sup> (ISO 2811)

**Viscosity:** 11-14 P (ROTOHINNER DIN 51550, 25° C)

**Application method:** Brush, roller or airless spray.

**Thinning:** 5-10% clean water.

**Spreading rates:** About 12m<sup>2</sup> per litre per coat on previously prepared surfaces.

**Drying times:** Touch dry after 1 hour and recoatable after 3 hours. Drying time depends on weather conditions (humidity, temperature).

**Colours:** It is available in White and in unlimited number of shades through **Vivechrom's** tinting system **CHROMOSYNTHESIS**.

**Storage:** Store between 5° and 40° C.

#### VOC (Volatile Organic Compounds)

EU limit value for this product category A/a  
Interior matt walls and ceilings (Gloss <25@60°): 30  
g/l (2010). This product contains max 10 g/l VOC.





# VIVE EMULSION

## Emulsion Paint for Interior Use

### SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.
- To fill and coat the surfaces: Use VIVECHROM's putty NEOPAL STUCCO.
- For new surfaces or porous surfaces coated with lime or low quality paints: Prime with VIVE PRIMER 100% ACRYLIC PRIMER FOR EMULSION PAINTS.
- For the refinishing of sound surfaces apply directly **VIVE EMULSION**.

### APPLICATION

- Thin with 5-10% clean water and stir well before use.
- Apply 2 coats of VIVE EMULSION.
- Ensure good ventilation during application and drying.
- Apply the paint and let it dry at temperatures between 10°C to 35°C.

### AFTER USE

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.

### HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Contains biocidal product: 1,2-benzisothiazol-3(2H)-one, reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1), and OIT. May produce an allergic reaction • Do not empty into drains • Dispose of contents and container in accordance with all national regulations • Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Poison Tel Center: 210 7793777 / for Cyprus: 1401

**STIR WELL BEFORE USE - PROTECT FROM FROST  
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**

