





TECHNICAL DATA SHEET Issue Date: 1/07/2022

11th Edition

DESCRIPTION

VIVELUX is a clear yacht varnish for exterior use that offers long lasting protection and enhances the natural beauty of wood. It can be applied to softwood and hardwood and it is highly recommended for yachts and every woodwork such as doors, windows, and frames. It contains UV filters to protect from the damaging effects of sunlight. It is easy to apply without sagging and gives a tough and elastic film, highly durable to adverse weather conditions.

PRODUCT INFORMATION

UV filter protection

High elasticity and endurance

Type: Wood varnish based on synthetic resins. Specific gravity: 0,92±0,01 gr/cm3 (ISO 2811) Viscosity: 3.5-6 ps (ROTOTHINNER DIN 51550, 25°C) Application method: Brush, roller. Thinning: Up to 3% v/v with VIVECHROM's BRUSH SOLVENT Spreading rates: About 12-17m² per litre per coat on previously prepared surfaces Drying times: Touch dry after 5 hours and recoatable after 24 hours. Drying time depends on weather conditions (humidity, temperature) Colours: It is available in colourless, gloss and satin Storage: Store between 5°C to 40°C.

VOC (VOLATILE ORGANIC COMPOUNDS)

EU limit value for this product of category A/e Interior/exterior trim varnishes and woodstains, including opaque woodstains: 400g/l (2010). This product contains max 399g/l VOC.





www.vivechrom.gr

Vivechrom Dr STEFANOS D. PATERAS SA

FACTORY & HEAD OFFICES: THESI VATHI PIGADI, 19600 MANDRA ATTICA, GREECE TEL.:+30 210 5538700, FAX:+30 210 5550464 1/2 THESSALONIKI: ETHN. ANTISTASEOS 114, 55134 KALAMARIA, TEL.:+30 2310 450000, FAX:+30 2310 493984





VIVELUX Yacht Varnish

SURFACE PREPARATION

- Surfaces must be clean and dry rubbed down with a suitable abrasive paper.
- On new or bare wood for best protection from fungi apply 1-2 coats of wood preservative VIVEXYL PLUS colourless or coloured.
- Treatments such as dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flatting should be used wherever possible. Work in well ventilated areas. Use suitable personal protection equipment.
- For maintenance of previously varnished surfaces apply one coat of **VIVELUX**.

APPLICATION

- Thin with up to 3% v/v with BRUSH SOLVENT and stir well before use.
- Apply 2 coats of VIVELUX in gloss or satin finish.
- Apply the paint and let it dry at temperatures between 10°C to 35°C.

AFTER USE - WASTE MANAGEMENT

Remove as much paint as possible from brushes and rollers before cleaning. Clean brushes and equipment with VIVECHROM'S BRUSH SOLVENT immediately after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

WARNING. Contains Hydrocarbons, alkanes • Flammable liquid and vapor • May cause drowsiness or dizziness • Keep out of reach of children • If medical advice is needed, have product container or label at hand • Keep away from heat, hot surfaces, sparks, open flames and other ignition sources • No smoking • Keep container tightly closed • Do not get in eyes, on skin, or on clothing • IF INHALED: Remove person to fresh air and keep comfortable for breathing • Call a POISON CENTER or doctor/physician if you feel unwell • Keep cool • Dispose of contents and container in accordance with all local, regional, national or international regulations • Repeated exposure may cause skin dryness or cracking. Poison Control Center for Greece: 210 7793777 / for Cyprus: 1401



www.vivechrom.gr

Vivechrom Dr STEFANOS D. PATERAS SA

 FACTORY & HEAD OFFICES:
 THESI VATHI PIGADI, 19600 MANDRA ATTICA, GREECE TEL.:+30 210 5538700, FAX:+30 210 5550464
 2/2

 THESSALONIKI:
 ETHN. ANTISTASEOS 114, 55134 KALAMARIA, TEL.:+30 2310 450000, FAX:+30 2310 493984
 2/2

STIR WELL BEFORE USE - PROTECT FROM FROST DO NOT APPLY AT TEMPERATURES UNDER 10°C.