

VIVEHARD

Hardener for VIVEMETAL



DESCRIPTION

VIVEHARD is a hardener for alkyd based enamel paints for professional use. Adding VIVEHARD to VIVEMETAL, drying is faster, a very hard dry film is achieved in short time, durability to hits is enriched. Colour and finish are also locked in even in the most adverse weather conditions.

High Toughness

Faster Drying

PRODUCT INFORMATION

Type: Isocyanate hardener for alkyd based enamel paints

Specific gravity: 1,030 ± 0,005gr/cm³ (ISO 2811).

Viscosity: 21-25sec (ASTM D1200 στους 25°C).

Mixing ratio: VIVEMETAL: VIVEHARD = 7:1 v/v.

Pot life: 4 hours

Colours: Colorless

VOC (Volatile Organic Compounds)

EU limit value for this product category
A/i one-pack performance coatings: 600g/l (2007)
and 500g/l (2010). This product contains max
440g/l.





VIVEHARD

Hardener for Vivemetal

APPLICATION

- Add to VIVEMETAL 10-15% v/v VIVEHARD
- Stir well and then apply the mixture.
- Use the mixture within 4 hours. After this time the mixture begins to thicken in the can.
- After opening the can, close it carefully and store it in a low humidity place.

AFTER USE

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

WARNING. Contains Cyclohexane, 5-isocyanato-1-(isocyanatomethyl)-1,3,3-trimethyl- homopolymer, n-Butyl acetate • Warning Flammable liquid and vapour • May cause an allergic skin reaction • May cause respiratory irritation • May cause drowsiness or dizziness • Keep out of reach of children • If medical advice is needed, have product container or label at hand • Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking • Keep container tightly closed • Do not get in eyes, on skin, or on clothing • IF INHALED: Remove person to fresh air and keep comfortable for breathing • Call a POISON CENTER or doctor if you feel unwell • Keep cool • Dispose of contents and container in accordance with all local, regional, national or international regulations • Contains isocyanates • May produce an allergic reaction • Repeated exposure may cause skin dryness or cracking.

Poison Control Center for Greece: +302107793777 / for Cyprus: 1401



**STIR WELL BEFORE USE - PROTECT FROM FROST
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**



www.vivechrom.gr