

NEOPAL® Stucco

Liquid stucco with high coverage



DESCRIPTION

NEOPAL STUCCO is a ready-to-use liquid putty, for covering and leveling interior walls from plaster, gypsumboards and concrete surfaces. It has very good working and leveling properties, as well as an excellent filling capacity. It dries fast and it is very easily sanded. It can be even more easily sanded with a sanding machine, without too much dust, minimizing irritation to eyes and inhaling problems. The result is a very smooth, flat and cohesive surface, ready to be recoated with emulsion or enamel paints.

PRODUCT INFORMATION

Easy to apply

Exceptional sanding

Type: Putty based on special resins.

Specific gravity:

Viscosity:

Application method: Knife or airless spray.

Application thickness: 0,5 – 2 mm totally, in one or two coats on sound surface. It has very good filling properties, filling flat gypsumboards, in one coat and normal joints of gypsumboards in two coats. For fine plaster, two coats are required.

Material consumption: About 1kg / m² per coat of 0,5 mm.

Drying times: For thin layers, drying and recoating are usually achieved after 4 hours. It can be sanded after 6-10 hours. Drying time depends on weather conditions (humidity, temperature), as well as on the thickness of the layer.

Storage life: 12 months (in temperatures from 5°C to 35°C).



www.vivechrom.gr



NEOPAL® Stucco

Liquid stucco with high coverage

SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.

APPLICATION

- Application with knife: NEOPAL STUCCO is ready-to-use. Thin slightly with water (less than 1 glass of clean water in 18kg) when the putty is applied under cold / damp conditions, as well as during the application of a second coat, whenever required.
- Application with airless spray: Thin with approximately 4- 6% w/w clean water, depending on the type of the airless gun, the pressure that can be achieved and nozzle diameter 27-35 thou. (millimeter of inch), depending on the manufacturer.
- NEOPAL STUCCO provides adequate time to the professional painter in order to correct any existing imperfection and it can also be flattened after 7 - 15 minutes, depending on the weather conditions, resulting in a great flat and smooth surface.
- After application and sanding, the surface should be primed with VIVECHROM's water based primer NEOPAL PRIMER ECO, thinned up to 50% with water. Finally the surface is coated with emulsion or enamel paints.
- Apply the paint and let it dry at temperatures between 10°C to 35°C.

AFTER USE

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Contains biocidal product: 1,2-benzisothiazol-3(2H)-one and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction • Do not empty into drains • Dispose of contents and container in accordance with all national regulations.

Poison Center for Greece: +30210 7793777 / For Cyprus: 1401

Lift with care – gross weight exceeds 10 kg.

**STIR WELL BEFORE USE - PROTECT FROM FROST
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**



www.vivechrom.gr