

STOKOS SPATOULARISMATOS

LEVELLING COMPOUND



DESCRIPTION

Vivechrom STOKOS SPATOULARISMATOS is an extremely fine-grained cement based powder stucco, reinforced with special acrylic resins. Used for levelling and smoothing of interior and exterior surfaces before painting (PRE-PAINT). It is suitable for walls and ceilings of plaster, plasterboard, bricks and it replaces oil stuccos and similar materials. By adding water, it creates a homogeneous, creamy paste with very good workability. It is applied softly and easily and it has very good filling properties and performance. It dries fast, it can be easily sanded and it doesn't crack nor shrink, giving a superb white, smooth surface. By adding VIVELATEX by Vivechrom to STOKOS SPATOULARISMATOS it reinforces its durability for exterior use.

Superb leveling

Exceptional filling

PRODUCT INFORMATION

Type: Cement based acrylic powder stucco.

Application method: Spatula, plaster trowel or airless spray

Mixing: For interior use: About 7,6-8lt clean water per 20kg STOKOS SPATOULARISMATOS powder or 1,9 -2 lt for 5 kg packs.

For exterior use: About 2lt VIVELATEX and 6lt clean water per 20kg STOKOS SPATOULARISMATOS or 0.5lt VIVELATEX and 1.5lt clean water per 5kg packs.

The pot life is about 2-3 hours with occasional stirring of the paste without adding water.

Spreading rates: About 1m²/kg per millimeter thick layer.

Drying times: Touch dry in 1-2 hours. Second layer after 3-4hr. These times vary depending on weather conditions (humidity, temperature) and the thickness of the layer.

Colours: It is available in white.

Storage - Shelf life: In covered dry place, preferably on pallets at temperatures from 5°C to 40°C, for 12 months since production date.

SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts. In case of plasterboards, it is recommended prior priming with Vivechrom's NEOPAL PRIMER thinned to 50% with water.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.





STOKOS SPATOULARISMATOS LEVELLING COMPOUND

APPLICATION

- Mix in 7,6-8lt pure water (or in mixture of 5.6-6lt clean water with 2lt VIVELATEX, in the case of exterior surfaces) gradually 20kg of STOKOS SPATOULARISMATOS powder, preferably with a mechanical stirrer, until it becomes homogenous. Leave the paste to rest for a bit before application. Stir regularly the paste to soften it, without further addition of water.
- The material is applied with a spatula in 2 or more coats to a total thickness that is recommended not to exceed 5mm.
- The time between the layers should be not less than 3-4 hours, depending on the temperature and humidity of the environment.
- The final layer can be sanded with fine sandpaper after 12 hours and then dusted.
- The surface must be thoroughly dry and before painting it needs to be primed with VIVECHROM's NEOPAL PRIMER thinned 50% with water for interior use or with ASTARI VIVEDUR thinned up to 100% with Vivechrom's BRUSH SOLVENT for exterior use.
- The putty is applied and allowed to dry at a temperature of 5°C to 35°C. If applied at temperatures above 35°C, before applying, the surface must be wetted with water.

AFTER USE

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.


HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

DANGER. Contains Portland cement • Causes serious eye damage • Causes skin irritation • Keep out of reach of children • If medical advice is needed, have product container or label at hand • Wear eye / face protection • Wash hands thoroughly after handling • IF IN EYES: Rinse cautiously with water for several minutes. Immediately call a POISON CENTER or doctor • Do not empty into drains • Dispose of contents and container in accordance with all national regulations.

Poison Center: +30210 7793777



STIR WELL BEFORE USE - PROTECT FROM FROST
DO NOT APPLY AT TEMPERATURES UNDER 10°C.

| | |
|--|---------------------------------|
|  | |
| VIVECHROM SA 19600 Mandra, Athens, Greece 13 | |
| DoP No: Vivechrom ΣΤΟΚΟΣ ΣΠΑΤΟΥΛΑΡΙΣΜΑΤΟΣ_2020-02 | |
| EN 998-1: 2010 | |
| Στόκος σπατουλαρίσματος γενικής χρήσης για εσωτερική χρήση - General purpose plastering mortar for internal use | |
| Αντιδραση στη φωτιά - Reaction to fire: | Class A1 |
| Πρόσφυση - Adhesion: | ≥ 0,5 N/mm ² , FP: B |
| Τριχοειδής απορρόφηση νερού - Water absorption: | W0 |
| Συντελεστής διάχυσης υδρατμών - Water vapour diffusion coefficient: | μ≤15 |
| Συντελεστής θερμικής αγωγιμότητας - Thermal conductivity (λ10,dry) | ≤ 0,35 W/mK |

