

VIVE PRIMER®

Waterbased Primer for Emulsion & Acrylic Paint



DESCRIPTION

VIVE PRIMER 100% Acrylic Primer for Emulsion Paints is a semitransparent waterbased primer for emulsion and acrylic paints. It is suitable for interior and exterior surfaces from plaster, concrete and walls leveled with putty. It has very good adhesion and penetration, great elasticity and durability to the alkaline surfaces, binding the surface effectively. It is applied easily and it has high spreading rate. It facilitates the workability and provides a uniform surface to the final coat.

For Internal & External Use

Very Good Adhesion

PRODUCT INFORMATION

Type: 100% acrylic waterbased primer.

Application method: Roller, brush or airless spray.

Thinning: 300 - 400% with clean water.


Spreading rates: About 15-20m² per litre per coat on previously prepared surfaces, depending on the percentage of thinning and surface absorption.

Drying times: Touch dry after less than 1 hour and recoatable after 2-3 hours. Drying time depends on weather conditions (humidity, temperature).

Storage: Store between 5° C to 40° C

VOC (Volatile Organic Compounds)

EU limit value for this product category A/g Primers: 30g/l (2010). This product contains max 5g/l VOC.



Our approach to sustainable business
akzonobel.com/sustainability

www.vivechrom.gr



VIVE PRIMER®

Waterbased Primer for Emulsion & Acrylic Paint

SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.
- To fill and coat the surfaces: Use NEOPAL STUCCO.

APPLICATION

Thin with 300-400% clean water and stir well before use.

In any case, you should thin the product in ratio 1 part VIVE PRIMER with 3-4 parts clean water so as to penetrate and blind the surface in depth, without creating a gloss film.

Apply 1 coat VIVE PRIMER.

Ensure good ventilation during application and drying.

Apply the paint and let it dry at temperatures between 10° C to 35° C.

AFTER USE – WASTE MANAGEMENT

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Contains biocidal product: 1,2-benzisothiazol-3(2H)-one and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction • Do not empty into drains • Dispose of contents and container in accordance with all national regulations.

Poison Tel Center: 210 7793777 / for Cyprus: 1401

**STIR WELL BEFORE USE - PROTECT FROM FROST
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**



www.vivechrom.gr