



## KNAUF SPATOULA FINE



Ready-mixed fine-grained white cement mortar based stucco reinforced with acrylic additives.

### **Product description**

**KNAUF SPATOULA FINE** is fine-grained white cement based stucco, reinforced with acrylic additives. **KNAUF SPATOULA FINE** is ideal for levelling and smoothing of interior and exterior surfaces. **KNAUF SPATOULA FINE** is suitable for plastered walls and ceilings and plasteboard. The material is classified as a type CSII-W0 mortar in accordance with the European standard EN 998-1.

### **Surface preparation:**

Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.

### **Order information:**

5 kg/bag – 180 bags/pallet  
Fine-grained: 629313  
20 kg/bag – 50 bags/pallet  
Fine-grained: 629313

### **Storage:**

The packed material must be well protected from humidity and rain, as it contains cement and various chemical admixtures.

For this reason, it must be stored in humidity-free spaces.

Under optimal storage conditions, the packed material can maintain its properties for 6 months from its production date which is shown on the packaging.

**KNAUF CYPRUS LTD**  
Christou Zeipekki 1, 4504 Vasa Kellakiou, T.Θ 54579 , 3725 | Limasol | Cyprus  
Tel.: +357 25821040, +357 25343371 Fax: +357 25343346  
e-mail: [knauf@knauf.com.cy](mailto:knauf@knauf.com.cy)  
<http://www.knauf.gr>





### **Application**

Mix in 15 L of clean water with gradually 20Kg preferably with a mechanical stirrer with low RPM, until it becomes homogenous. Leave the paste to rest for approximately 5 min and restore without adding any water until a homogenous creamy paste is obtained. The material is applied with a spatula in at least 2 layers at a total thickness of not more than 5mm. The final layer must be sanded with fine sandpaper and dusted and after the application of a primer is ready to receive the paint coats.

### **Water consumption**

Approximately 15 L water per 20Kg bag.

### **Coverage**

Approximately 1-1.2Kg/m<sup>2</sup>, depending on the substratum kind its flatness as well as the demanded results.

### **Storage**

If material is stored in a dry covered environment on wooden pallets at a temperature between 5°C and 40°C a product life of 6 months from production date is granted.

**KNAUF SPATOULA FINE** is produced in Cyprus in full compliance with the safety and environmental regulations of the European Union, under the strict quality control of Knauf

Essential characteristics	Performance	Harmonized standard
Reaction to fire	A1	CYS EN 998-1:2016
Adhesion	0.2N/mm <sup>2</sup> FP:A	
Compressive strength	CS I	
Water absorption	W0	
Water vapour diffusion coeff	μ25	
Thermal conductivity	0,83 W/m·K for P = 50% 0,93 W/m·K for P = 90% ( tab. mean value)	
Durability (against freeze / thaw)	Evaluation based on provisions valid in the intended place of use of the mortar	

**KNAUF CYPRUS LTD**  
Christou Zeipekki 1, 4504 Vasa Kellakiou, T.Θ 54579 , 3725 | Limasol | Cyprus  
Tel.: +357 25821040, +357 25343371 Fax: +357 25343346  
e-mail: [knauf@knauf.com.cy](mailto:knauf@knauf.com.cy)  
<http://www.knauf.gr>

