



PregyFlam BA/BD 15

PREGYFLAM BA/BD 13 tapered (BA) or squared (BD) edges gypsum plasterboard. Thickness 15 mm. For high fire resistance.

Siniat Technical Department provides support to design and installation phases with advice

in the context of static, acoustic, thermal and protection to fire according to the existing rules.

Technical Data

WIDTH (TOLERANCE 0/-4 MM)	1200 mm
LENGTH (TOLERANCE 0/-5 MM)	2000, 2500, 3000 mm
EDGES	BA (Tapered Edges) BD (Squared Edges)
THICKNESS (TOLERANCE 0/-5 MM)	15 mm
DENSITY AVERAGE VALUE (*)	893 Kg/m ³
WEIGHT AVERAGE VALUE (*)	13,4 Kg/m ²
SURFACE HARDNESS	< 15 mm (Impact diameter)
FLEXION RESISTANCE LONGITUDINAL	
MINIMUM VALUE FOR DESIGNING	650 N
AVERAGE VALUE (*)	830 N
FLEXION RESISTANCE TRANSVERSAL	
MINIMUM VALUE FOR DESIGNING	250 N
AVERAGE VALUE (*)	435 N
THERMAL CONDUCTIVITY (LITERATURE VALUE)	$\lambda = 0,21 \text{ W/mK}$
FIRE REACTION	A2-s1, d0(B)
INTENDED USES	walls, partitions, linings and ceilings.

(*) the average values are referred to those of production and are indicative

EUROPEAN STANDARD:
UNI EN 520.

TYPE OF BOARD:
D, F and I – on the base of Initial Type Test (ITT)

Contatti
ETEX BUILDING PERFORMANCE S.P.A.
Via Perlasca, 14
27010 Vellezzo Bellini (PV)
Tel. +39 0382 45 75 75
Fax +39 0382 45 75 250
siniat.italia@siniat.com

www.siniat.it